OPERA

Technical sheet

DICKSON®

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		
GENERAL CHARACTERISTICS				
Composition	100% solution dyed acrylic			
Finish	Cleangard special dirt-resistance and awning water resistant treatment			
Weave	Jacquard			ISO 7211-1
Weight	330		g/m²	ISO 3801
Thickness	0.67		mm	ISO 5084
Width	120		cm	EN 1773
Roll length	60		ml	
FABRIC RESISTANCE				
Tensile strength	180	90	daN/5cm	ISO 13934-1
Elongation at break	25	26	%	ISO 13934-1
Tear strength	5.3	3	daN	ISO 13937-1
Stiffness	3000	1300	mN	ISO 2493
Schmerber	200		mm	ISO 811
Spray test	5		class /5	ISO 4920
Oil-resistant properties	4		class /8	ISO 14419
Resistance durability	4		class /4	EN 13561
COLOUR-FASTNESS				
Colour fastness UV - outdoor - 1000h	4-5		class /5	ISO 105 B04
Colour fastness UV - indoor	7-8		class /8	ISO 105 B02
Colour fastness under dry friction	5		class /5	ISO 105X12
Colour fastness under wet friction	5		class /5	ISO 105X12
Colourfastness	4		class /4	EN 13561
USES				
Guarantee	10		years	
Recommended use	Drop arm awning, Folding arm awning, Exterior velum, Pergola, Sail shade			

This product's values may vary with a tolerance of ± 5%

FINISHING CLEANGARD® OUTDOOR TREATMENT by DICKSON®

SUNACRYL® OUTDOOR FIBRE by DICKSON®

OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 CQ 638/2 IFTH
Tested for harmful substances.
www.oeko-tex.com/standard100

ISO 9001
ISO 14001
OHSAS 18001
BUREAU VERITAS Certification

WARRANTY 10 YEARS

WARRANTY MASS DYED COLOURS

MADE IN FRANCE

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration
10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France
Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK